

PRODUCT SPECIFICATION

Grade **MM 1300** (Non Watermarked)

Ryo Base Paper

Recipe 100% Wood Pulp -

Properties	Unit	Target	Min	Max	CV%max	Test Method	Comments
Grammage	%	13,5	13	14		ISO 536	
Thickness	pm	210	180	240	-	ISO 20534	On 10 layers
Permeability	CU	10				ISO 2965	
Filler	%			-	-	DIN 54370	
Tensile Strength	daN/30mm	3.3	3			ISO 1924	
Stretch	%	1.4	1			ISO 1924	
Whiteness	%	76	73		-	ISO 2470	
Opacity	%	21	19	24	-	ISO 2471	
Humidity	%	3.5		-		OnLine	

- Characteristics determined in conditioned laboratory - 50% RH / T = 23° /ISO 187.

Remarks

Tolerances (Min & Max) are given for the average, obtained on a mother roll